

1217M0126

Grès cérame Mélodie Oslo - Cendre -  
300x600x10 ( 298x598) rectifié R10B -1.08m<sup>2</sup> -20.83 kg V2

TEST		RESULT
UNE-EN ISO 10545-2	DIMENSIONAL FEATURES	COMPLIES WITH THE STANDARD
UNE-EN ISO 10545-3	WATER ABSORPTION	<= 0,5 %
UNE-EN ISO 10545-4	MODULUS OF RUPTURE - BREAKING STRENGTH	1600-2400 N
	MODULUS OF RUPTURE - BENDING STRENGTH	35-45 N/mm <sup>2</sup>
UNE-EN ISO 10545-6	RESISTANCE TO DEEP ABRASION (MM <sup>3</sup> )	< 130 mm <sup>3</sup>
UNE-EN ISO 10545-7	RESISTANCE TO SURFACE ABRASION	NOT APPLY
UNE-EN ISO 10545-8	LINEAR THERMAL EXPANSION	<7,0 x 10 <sup>-6</sup> °C <sup>-1</sup>
UNE-EN ISO 10545-9	THERMAL SHOCK RESISTANCE	RESISTS
UNE-EN ISO 10545-11	CRAZING RESISTANCE	RESISTS
UNE-EN ISO 10545-12	FROST RESISTANCE	RESISTS
UNE-EN ISO 10545-13	CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L	A
	CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L	A
	CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%	COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - CITRIC ACID 100 G/L	COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L	COMPLIES WITH THE STANDARD
UNE-EN ISO 10545-14	STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL	5
	STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL	5
	STAIN RESISTANCE - OLIVE OIL	5



Page 1/2

Document et photos non-contractuels. Tarif selon la date d'exportation du pdf, mentionné à titre indicatif. Les dimensions en millimètres s'entendent sous réserve des tolérances d'usine, d'éventuelles modifications ultérieures, de même que de nouvelles possibilités de montage. La responsabilité ne peut être engagée en cas de cotes manquantes ou erronées (CO art. 100)

MAGENTA Home Design SA  
www.magenta-sa.ch  
+ 41 848 308 308



Lausanne • Showroom & Administration  
Chemin de Mongevon 2  
1023 Crissier (VD)

Genève • Showroom  
Chemin du Château-Bloch 11  
1219 Le Lignon (GE)

Entrepôt - Logistique  
Chemin de la Gottrause 5-7,  
1023 Crissier (VD)

## SLIP RESISTANCE

TEST		RESULT
UNE 41901:2017 EX	SLIP RESISTANCE (PENDULUM)	CLASE 1
DIN 51130	CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)	R10
DIN 51097	CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS	-
(PTV) DRY	CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) DRY	Low
(PTV) WET	CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET	Low
ANSI A326.3	DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.	-

TEST		VALOR UPEC
	UPEC CERTIFICATION	-



Document et photos non-contractuels. Tarif selon la date d'exportation du pdf, mentionné à titre indicatif. Les dimensions en millimètres s'entendent sous réserve des tolérances d'usine, d'éventuelles modifications ultérieures, de même que de nouvelles possibilités de montage. La responsabilité ne peut être engagée en cas de cotes manquantes ou erronées (CO art. 100)

MAGENTA Home Design SA  
www.magenta-sa.ch  
+ 41 848 308 308



Lausanne • Showroom & Administration  
Chemin de Mongevon 2  
1023 Crissier (VD)

Genève • Showroom  
Chemin du Château-Bloch 11  
1219 Le Lignon (GE)

Entrepôt - Logistique  
Chemin de la Gottrause 5-7,  
1023 Crissier (VD)